

VOC Regulatory Compliance:



Division of Sierra Corporation ISO 9001-2008 CERTIFIED

TK-SILOXANE DYE Pigmented Water Repellent

Item No. TK-5765 series

PRODUCT DESCRIPTION

TK-SILOXANE DYE is a specially formulated pigmented waterproofing treatment for producing uniformly colored concrete surfaces that are water and chemically resistant.

Features:

- Disguises and blends discolored or unevenly colored surfaces to produce a uniform and attractive finish.
- Protects the surface against damaging effects of water intrusion, acid rain, deicing chemicals, freeze/thaw exposure, airborne dirt, smog, industrial fumes, and most other atmospheric chemicals.

USES:

Suitable for interior or exterior use on concrete driveways, walkways, patios, floors or any horizontal cementitious surface.

APPLICATION PROCEDURES:

All surfaces to be treated must be clean and structurally sound.

PREPARATION:

Thoroughly clean surfaces to remove all grease, oils, form oils or other contaminants. Best results are obtained by applying TK-SILOXANE DYE to dry surfaces. It is recommended that surface temperatures be 40°F or above at the time of application to ensure that surfaces are frost-free. A test patch should always be performed to determine proper results and coverage rates prior to application.

MIXING:

- 1) Because its color pigments will settle softly during storage, TK-SILOXANE DYE should be mechanically mixed for 2-5 minutes prior to application.
- 2) If stirring without removing the container lid is desired, TK-SILOXANE DYE may be mixed by inserting a stir whip mixer through the bunghole in the lid. Stir for 2-5 minutes.
- 3) Mix the product occasionally throughout the application process to help keep pigments suspended.

APPLICATION:

Apply liberally by spray at a coverage rate of approximately 150 square feet per gallon, or in sufficient quantity to completely satisfy the porosity of the concrete. Follow by immediate back rolling in all directions in order to uniformly distribute pigments throughout the application area. Continue rolling until the product is adequately distributed and any liquid on the surface ceases to move.

CLEAN UP:

Clean tools, equipment and spills with TK-00 XYLENE*. Pump solvent through spray equipment to remove residue which can clog the hose and wand assembly.

COVERAGE:

Typical coverage rate is 100-150 square feet per gallon. If a second coat is desired, it should be applied at the same rate. Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

LIMITATIONS:

- TK-SILOXANE DYE will not penetrate wet or frozen substrates. Apply in temperatures above 40°F to ensure the concrete is frost free. Colder weather applications may be made under prescribed conditions and procedures specified by TK Products.
- Do not apply if rain is expected within 24 hours of application.
- Not for use on asphalt or surfaces subject to immersion or constant liquid contact.
- As with all colored coatings, TK-SILOXANE DYE is a maintenance item that will require occasional recoating (how often will be dependent on the degree of use).

FIRST AID:

 Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

TK-SILOXANE DYE is available through TK Distributors. Contact TK Products for the nearest distributor. Available in standard and custom color options. Contact your representative for color availability and pricing. Packaged in 5-gallon pails and I-gallon cans. Multiple containers will be combined where appropriate.

FOR PROFESSIONAL USE ONLY

NOTES:

*TK-00 XYLENE must be purchases separately

04/15 Last Rev. 03/15

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express of implied, including implied warranties of merchantability or fitness for a particular purpose. SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, ORAT ITS OPTION, REFUNDTHE PURCHASE PRICE. THIS ISTHE SOLEAND EXCLUSIVE REMEDY FOR ANY FAILURE OFTK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.

